

# PRODUCT INFORMATION

## REGUPOL solar glue




### Application

Protection layer on flat roofs underneath Solar Systems

### Product

|                 |   |
|-----------------|---|
| Name of Product | <b>REGUPOL solar glue</b>   |
| Color           | black   |
| Material        | elastic premanufactured mat made from selected rubber bound with polyurethane, self-adhesive lamination |
| Thickness       | 8 mm  |

### Technical Data

|   |   |   |
|---|---|---|
| Specific Weight                                       | 780 kg/m <sup>3</sup>   |   |
| Weight per m <sup>2</sup>                             | 6.24 kg   |   |
| Tensile Strength<br>(without lamination)              | 0.65 N/mm <sup>2</sup>  | following<br>DIN EN ISO 1798  |
| Elongation at Break<br>(without lamination)           | 55 %  | following<br>DIN EN ISO 1798  |
| Stress at 25 %<br>Compression<br>(without lamination) | 0.70 N/mm <sup>2</sup>  | DIN EN ISO 3386-2   |
| Temperature Resistance                                | - 40° C up to 90° C   |   |
| Fire Resistance                                       | Class E   | DIN EN 13501-1  |
| Certification   |  | Cradle to Cradle Certified® is a registered trademark of the Cradle to Cradle Products Innovation Institute (C2CPII). <b>REGUPOL solar glue</b> is Cradle to Cradle Certified® at the Bronze level. |

**Notice:** The above-mentioned test data are based on periodical laboratory testing of test specimen taken from the actual manufacturing process and show the average values measured. The publishing of these technical data does not relieve the user of the necessity to test the relevant product for physical fitness based on a specific application. As the final use and application of our products are out of our control, this is the sole responsibility of the buyer / end user. All of our products do carry a warranty against manufacturer's defects according to our standard terms and conditions of sale. Due to deviations in raw materials, external influences like temperature and humidity variations, and the fact that this data relates to a resilient material the above-mentioned values are subject to vary up to +/- 25%.